

Zochem LLC (Zochem South)
600 Printwood Drive
Dickson, TN 37055, USA
CustomerService@Zochem.com
PHONE (615) 446-8791
FAX (615) 446-8789



Zochem ULC (Zochem North)
1 Tilbury Court, Brampton
Ontario, L6T 3T4, Canada
CustomerCare@Zochem.com
PHONE (800) 324-1806
FAX (905) 453-2920

TECHNICAL DATA SHEET

ZINC OXIDE GRADE 103

Description

Our Zinc Oxide product is a brilliant white powder manufactured by the French (Indirect) Process.

Grade 103 offers very high purity, large particle size, and the lowest m²/g surface area ("SA") available in high quality French Process product.

Grade 103 replaces grades Zinc Oxide LLC 800XL, KADOX 930, and KADOX XX503R

Grade 103 is also a drop in substitute for American (Direct) Process zinc oxide in most applications.

Uses

This grade is used where a very low impurity large particle size zinc oxide is required such as in electronic soft ferrites, varistors, ceramics, and paint and coatings.

This product is also available in pelleted form (grade 103P), and with around up to 0.1% processing aid/surface treatment (grade 103T) for some rubber mixers

REPRESENTATIVE CHEMICAL PROPERTIES

Chemical Analysis (%)	Typical Limit**	Nominal	Test Method
Zinc Oxide (ZnO) ignited basis	99.8 min	99.9	Supplier (calculation)
Lead (Pb) *	0.003 max	0.002	ASTM D4075
Cadmium (Cd) *	0.002 max	0.0003	ASTM D4075
Iron (Fe)	0.002 max	0.0003	ASTM D4075
Copper (Cu)	0.001 max	0.0001	ASTM D4075
Loss at 110°C (moisture)	0.25 max	0.15	ASTM D280

REPRESENTATIVE PHYSICAL PROPERTIES

Surface Area (m ² /g) *	2 - 4	3.2	ASTM D4315
Particle Size (microns)	0.2 - 0.6	0.3	Supplier (calculation)
Fineness retained on 325 mesh (%) *	0.02 max	0.005	ASTM D185
(Fineness passing through 325 mesh (%) Specifications	99.98 min	99.995	ASTM D185) ASTM D79

* Regular test item for process & product control and included on COA. Other items are for reference only.

** Zochem can produce zinc oxide to customer specifications superseding the above table.

Standard Packaging: 50 lb. Kraft paper bags on 2,000 to 2,500 lb net wt pallet, or 2,000 lb FIBC.